



Product Description:

Ezeerip is produced from **75-micron monoaxially oriented polypropylene (MOPP) film** and coated with a newly formulated pressure-sensitive adhesive. It is suitable for easy opening of packaging including corrugated cases, fibreboard cartons, envelopes, paper sacks, and e-commerce mailers.

Product Specifications:

Properties	Test Method	Unit	Specification
Tape width tolerance	Bagla Internal Method	mm	± 0.1
Total tape thickness	AFERA 5006	µm	100 ± 10
Film Thickness	AFERA 5006	µm	75 ± 5
Glue Thickness	Weight	GSM	25 ± 2
Breaking strength	AFERA 5004	N/cm	≥54
Elongation at break	AFERA 5004	%	≥30
Tensile strength at break	AFERA 5004	kgf/mm ²	≥36
Peel adhesion to stainless steel	FINAT FTM 1	gf/25mm	≥800
Loop tack to glass	FINAT FTM 9	gf/25mm	≥800

Standard Putups

- **Width:** 2mm to 30mm
- **Length:** 5,000m to 1,20,000m
- **Core ID:** 76mm, 152mm
- **Colors:** Clear + Multiple Colors
- **Wounding:** Traverse wound

Features

- Rips easily through most grades of fluting and board.
- Enhances product strength & reinforces the weaker areas
- Utilise print for increased consumer engagement

Applications

- Opening of corrugated boxes & fibreboard cartons
- Ideal for solid fiberboards ranging from 200–600 g/m²

Additional Information

SHELF LIFE: The standard shelf life is 12 months from the date of manufacture. However, this depends on several factors such as storage conditions, handling etc.

DISPOSAL: Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

STORAGE: Storage below 32°C (90°F) is recommended.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.