

BX-Bio is made with special patented additives to make the film biodegradable complying with relevant industry standards that allow the film to break down in natural conditions after 2-3 years, as confirmed by the supplier of additives and evidenced in the reports by various international laboratories. It decomposes in the presence of bacteria and other microorganisms under natural conditions, producing water, CO2, and biomass. It is designed to return safely to the environment so it should be the preferred choice for anyone looking to 'go green.

SIGNIFICANT PROPERTIES



General Properties

- Contains an additive that initiates chemical breakdown more quickly and completely in the presence of oxygen and heat or UV light.
- Extensive abuse resistance of the film helps the products survive rough handling and damages due to multi-packaging.
- Exhibits superior transparency and gloss enhancing product appearance.



Sealing Properties

- Ensures strong & durable seals
- Operates on a wide sealing temperature range
- Superior ease of use manually as well on high-speed automatic shrink equipment.



Shrinking Properties

- Balanced shrink for tight and crisp packages.
- High burnout resistance enables sealing on multiple-end seal systems.
- Clean shrink appearance with excellent conformity of shrinkage & minimum dog-ears.
- Easy to run on most types of equipment.

Bagla Group Shrink Films comply with the requirements and regulations of FDA and USDA which states that materials may be used in food contact applications.

STANDARD PUT-UPS

- Available Thickness: 50, 60, 75 and 100 gauge as cross-linked and non-cross linked variants.
- Single Wound Flat Film is available in custom widths from 3" to 100" in 1/4" increments.
- Center Folded Film is available in custom widths from 3" to 50" in 1/2" increments.
- Shrink Pouches are available in lengths of 4" to 80" and openings of 4" to 40".
- Center Folded Film has half the linear footage of single-wound flat film for the same thickness (in gauge) and roll dimensions.

APPLICATIONS

- Retail packaging
- Industrial packaging
- Pallet wrapping
- Bundling, Multipacking & Unitizing Products
- Medical Packaging

TECHNICAL SPECIFICATIONS

Duanautiaa	ASTM Test Method	Unit	Thickness (gauge)			
Properties		Offic	50	60	75	100
Haze (avg)	D1003	%	2.2	2.3	2.4	2.6
Gloss (at 20°) (min)	D2457	GU	135	130	130	125
COF, Kinetic	D1894	-	0.26	0.26	0.23	0.2
Shrinkage, 102°C (216°F)10 min	D1204	% area	65	65	65	65
Shrink Force (100°C)	D2838	g/in	95	110	130	160
Stiffness Modulus (avg)	D882	Kpsi	37	37	37	37
Tensile Strength (avg)	D882	Kpsi	13	13	13	13
Elongation (avg)	D882	%	120	125	130	135
Tear Strength (avg) (Elmendorf)	D1922	g	20	25	30	35
Spencer Impac	D3420	lbf	8	9.5	11	15
WVTR	F1249	g/100 in ² /24 hr	2.3	2.5	2	1.5
Oxygen Transmission	D3985	cc/100 in²/24 hr	1000	900	800	600
CO2 Transmission	D1434	cc/100 in ² /24 hr.	2500	2400	2200	1950

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting pecifications. Values are based on initial production and tests run during development of this film.

BX-Bio - Linear Footage of Center Folded Shrink Film

Core I.D.	Roll O.D.	Length (feet)						
(Inches)	(Inches)	50 guage	60 guage	75 guage	100 guage			
3	91/2	5,826	4,370	3,500	2,624			
3	13	11,652	8,740	7,000	5,248			
6	11	5,826	4,370	3,500	2,624			
6	14	11,652	8,740	7,000	5,248			
6	18 ^{3/4}	23,304	17,480	14,000	10,496			

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in gauge) and roll dimensions.

DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill













STORAGE



Fahrenhiet) is recommended.



• Storage below 32 degrees Celsius (90 degrees

DISCLAIMER

Bagla® films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

Head Office

• New Delhi, Delhi

Factories

- 3 in Mundra, Gujarat, India
- 2 in Roorkee, Uttrakhand, India
- 1 in Ghaziabad, Uttar Pradesh, India

Domestic Sales Office

- Delhi Mumbai Kolkata Cochin
- Banglore Hyderabad Chennai Bhopal

International Sales Office

- Spain USA Australia United Kingdom
- Argentina South Africa Egypt
- Poland Germany Canda

