

# BX-Opaque

Low Energy Shrink Film



BX-Opaque is the perfect solution for products that require privacy or security during transportation or storage. With its opaque properties, the packed product is almost completely concealed, maintaining its confidentiality, and eliminates the cost of cartons and fillers. When it comes to protecting your products from dust and moisture, and ensuring their privacy, BX-Opaque is a great choice!

## SIGNIFICANT PROPERTIES

### General Properties

- Attractive colours: White, Grey, and Brown
- Blocks nearly 100% of UV light.
- Ensures confidentiality of the product (up to 90% opacity)
- Can be printed or used with labels.

### Sealing Properties

- Ensures strong & durable seals
- Operates on a wide sealing temperature range
- Requires little or no cooling dwell time
- Compatible with most sealing machines

### Shrinking Properties

- Excellent cleanup for tight, attractive packages
- High shrink force conforms to irregular shapes
- Exceptional bundling capabilities
- Excellent resistance to burn-through

Bagla Group Shrink Films comply with the requirements and regulations of FDA and USDA which states that materials may be used in food contact applications.

## STANDARD PUT-UPS

- Available Thickness: 20, 38 microns as cross-linked and non-cross linked variants.
- Single Wound Flat Film is available in custom widths from 75mm to 2000mm in 6.5mm increments.
- Center Folded Film is available in custom widths from 75mm to 1000mm in 13mm increments.
- Shrink Pouches are available in lengths of 100mm to 2000mm and openings of 100m to 1000mm
- Center Folded Film has half the linear footage of single-wound flat film for the same thickness (in microns) and roll dimensions.

## APPLICATIONS

- Expensive products such as jewellery, electronics, etc.
- Confidential official documents, catalogues, etc.
- Pharmaceuticals and supplements
- E-commerce shipping products.

# TECHNICAL SPECIFICATIONS

Properties	ASTM Test Method	Unit	Thickness (Micron)	
			25	37
Haze	D1003	%	5.0	5.2
Gloss at 20°	D2457	GU	110	100
COF, Kinetic	D1894	-	0.2	0.2
Transmittance	D1003-13	%	5.5	2.5
Shrink Force (100°C)	D2838	N/mm	0.04	0.071
Stiffness Modulus (avg)	D882	MPa	282	282
Tensile Strength (avg)	D882	MPa	124	124
Elongation (avg)	D882	%	125	125
WVTR	F1249	g/h.m <sup>2</sup> /24 hr	6.97	6.97
Oxygen Transmission	D3985	cc/m <sup>2</sup> /24 hr	56.3	37.4
PIR Content	Internal	%	30	30

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

## BX-UltraOpaque - Linear Footage of Center Folded Shrink Film

Core I.D. (mm)	Roll O.D. (mm)	Length (Meter)	
		25µm	37µm
76	242	800	533
76	330	1,600	1,067
152	280	800	533
152	356	1,600	1,067
152	476	3,200	2,134

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in micron) and roll dimensions.

## DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill

## STORAGE

- Storage below 32 degrees Celsius (90 degrees Fahrenheit) is recommended.



## DISCLAIMER

Bagla® films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

### Head Office

- New Delhi, Delhi

### Domestic Sales Office

- Delhi • Mumbai • Kolkata • Cochin
- Bangalore • Hyderabad • Chennai • Bhopal

### International Sales Office

- Spain • USA • Australia • United Kingdom
- Argentina • South Africa • Egypt
- Poland • Germany • Canada

- 3 in Mundra, Gujarat, India
- 2 in Roorkee, Uttar Pradesh, India
- 1 in Ghaziabad, Uttar Pradesh, India