



BX Earth - 60 represents a significant leap forward in sustainable packaging solutions. This innovative film incorporates 60% Post Consumer Recycled (PCR) Content, reducing reliance on virgin plastic and minimizing environmental footprint. Additionally, it boasts AENOR Certification, a testament to its compliance with stringent European regulatory standards.

## SIGNIFICANT PROPERTIES

### General Properties

- High gloss, clarity, and transparency
- Good tear resistance provides a safe & durable wrap on products
- High tensile strength makes it suitable for product bundling
- Compatible with all Shrink Wrap Machines

### Sealing Properties

- Ensures strong & durable seals
- Operates on a wide sealing temperature range
- Superior ease of use manually as well on high-speed automatic shrink equipment.

### Shrinking Properties

- High shrink force for bundling and multipacking.
- Superior puncture resistance to protect your products effectively.
- Excellent shrink performance for secure and tamper-evident seal.

Bagla Group Shrink Films comply with the requirements and regulations of FDA and USDA which states that materials may be used in food contact applications.

## STANDARD PUT-UPS

- Available Thickness: Available Thickness: 40, 45, 60, 75, 100, 120, 150 gauge in Cross Linked Variants and 50, 60, 75, 100, 120, gauge in non cross linked variants
- Single Wound Flat Film is available in custom widths from 3" to 100" in 1/4" increments.
- Center Folded Film is available in custom widths from 3" to 50" in 1/2" increments.
- Shrink Pouches are available in lengths of 4" to 80" and openings of 4" to 40".

## APPLICATIONS

- Retail packaging
- Industrial packaging
- Bundling, Multipacking & Unitizing Products



# TECHNICAL SPECIFICATIONS

Properties	ASTM Test Method	Unit	Non-Cross Linked POF Shrink Film Thickness (gauge)				
			50	60	75	100	120
Haze	D1003	%	3	3.2	3.4	3.6	3
Gloss at 20°	D2457	GU	125	115	115	115	130
COF, Kinetic	D1894	gf	0.15	0.15	0.15	0.15	0.15
Shrinkage, 102°C (216°F)--10 Min	D1204	%(area)	50	50	50	50	50
Shrink Force (100°C)	D2838	g/in	130	130	145	160	200
Stiffness Modulus (avg)	D882-80	kpsi	60	60	60	55	55
Tensile Strength (avg)	D882	kpsi	13	13	13	13	13
Elongation (avg)	D882	%	120	120	140	140	160
WVTR	F1249	g/100 in <sup>2</sup> /24hr	1.91	1.52	1.179	0.93	1
Oxygen Transmission	D3985	cc/100 in <sup>2</sup> /24hr	527	431	344	333	400
PCR Content	Internal	%	60	60	60	60	60

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

## BX-Earth - Linear Footage of Center Folded Shrink Film

Core I.D. (Inches)	Roll O.D. (Inches)	Length (feet)				
		50 gauge	60 gauge	75 gauge	100 gauge	120 gauge
3	9 <sup>1/2</sup>	5,250	4,375	3,500	2,625	2,100
3	13	10,500	8,750	7,000	5,250	4,200
6	11	5,250	5,830	4,375	3,500	2,625
6	14	10,500	11,660	8,750	7,000	5,250
6	18 <sup>3/4</sup>	21,000	23,320	17,500	14,000	10,500

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in gauge) and roll dimensions.

## DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill

## STORAGE

- Storage below 32 degrees Celsius (90 degrees Fahrenheit) is recommended.



## DISCLAIMER

Bagla® films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

### Head Office

- New Delhi, Delhi

### Factories

- 3 in Mundra, Gujarat, India
- 2 in Roorkee, Uttar Pradesh, India
- 1 in Ghaziabad, Uttar Pradesh, India

### Domestic Sales Office

- Delhi • Mumbai • Kolkata • Cochin
- Bangalore • Hyderabad • Chennai • Bhopal

### International Sales Office

- Spain • USA • Australia • United Kingdom
- Argentina • South Africa • Egypt
- Poland • Germany • Canada