





BX-Earth represents a significant leap forward in sustainable packaging solutions. This innovative film incorporates 60% Recycled Content, reducing reliance on virgin plastic and minimizing environmental footprint. Additionally, it boasts AENOR Certification, a testament to its compliance with stringent European regulatory standards.

# SIGNIFICANT PROPERTIES



# **General Properties**

- High gloss, clarity, and transparency
- Good tear resistance provides a safe & durable wrap on products
- High tensile strength makes it suitable for product bundling
- Compatible with all shrink wrap Machines



# Sealing Properties

- Ensures strong & durable seals
- Operates on a wide sealing temperature range
- Superior ease of use manually as well on high-speed automatic shrink equipment.



# **Shrinking Properties**

- High shrink force for bundling and multipacking.
- Superior puncture resistance to protect your products effectively.
- Excellent shrink performance for secure and tamper-evident seal.

## STANDARD PUT-UPS

- Available Thickness: Available Thickness: 40, 45, 60, 75, 100, 120, 150 gauge in Cross Linked Variants and 50, 60, 75, 100, 120, gauge in non cross linked variants
- Single Wound Flat Film is available in custom widths from 3" to 100" in 1/4" increments.
- Center Folded Film is available in custom widths from 3" to 50" in 1/2" increments.
- Shrink Pouches are available in lengths of 4" to 80" and openings of 4" to 40".
- Contains 30% certified post-consumer recycled (PCR) content.
- Contains 30% certified post-industrial recycled (PIR) content.

# **APPLICATIONS**

- Retail packaging
- Industrial packaging
- Bundling, Multipacking & Unitizing Products





# **TECHNICAL SPECIFICATIONS**

Droportion	ASTM Test Method	Unit	Cross Linked POF Shrink Film Thickness (gauge)						
Properties			40	45	60	75	100	120	150
Haze	D1003	%	2	2	2.5	2.5	3	3	3
Gloss at 20°	D2457	GU	135	135	135	135	130	130	130
COF, Kinetic	D1894	gf	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Shrinkage, 102°C (216°F)10 Min	D1204	%(area)	50	50	50	50	50	50	50
Shrink Force (100°C)	D2838	g/in	80	85	130	145	160	200	240
Stiffness Modulus (avg)	D882	kpsi	60	60	60	60	55	55	50
Tensile Strength (avg)	D882	kpsi	15	15	15	15	15	15	15
Elongation (avg)	D882	%	125	130	145	150	160	160	170
WVTR	F1249	g/100 in <sup>2</sup> /24hr	1.9	2.1	1.5	1.4	1	0.9	0.8
Oxygen Transmission	D3985	cc/100 in²/24hr	855	900	600	500	400	400	300
PCR Content	Internal	-	30	30	30	30	30	30	30
PIR Content	Internal	-	30	30	30	30	30	30	30

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

#### **BX-Earth - Linear Footage of Center Folded Shrink Film**

Core I.D.	Roll O.D. (Inches)	Length (feet)							
(Inches)		40 guage	45 guage	60 guage	75 guage	100 guage	120 guage	150 guage	
3	9 <sup>1/2</sup>	6,560	5,830	4,375	3,500	2,625	2,180	1,750	
3	13	13,120	11,660	8,750	7,000	5,250	4,360	3,500	
6	11	6,560	5,830	4,375	3,500	2,625	2,180	1,750	
6	14	13,120	11,660	8,750	7,000	5,250	4,360	3,500	
6	18 <sup>3/4</sup>	26,240	23,320	17,500	14,000	10,500	8,720	7,000	

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in gauge) and roll dimensions.

## **DISPOSAL**

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill













**STORAGE** 



Fahrenhiet) is recommended.



• Storage below 32 degrees Celsius (90 degrees

# **DISCLAIMER**

Bagla® films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

## **Head Office**

• New Delhi, Delhi

#### **Factories**

- 3 in Mundra, Gujarat, India
- 2 in Roorkee, Uttrakhand, India
- 1 in Ghaziabad, Uttar Pradesh, India

#### **Domestic Sales Office**

- Delhi Mumbai Kolkata Cochin
- Banglore Hyderabad Chennai Bhopal

## **International Sales Office**

- Spain USA Australia United Kingdom
- Argentina South Africa Egypt
- Poland Germany Canada

