


# BX-Tinted

Tinted Shrink Film



**BX-Tinted** polyolefin shrink film is the perfect solution for your packaging needs. Its advanced cross-linked technology with tint properties ensures robust and long-lasting packaging for all types of products. This versatile film is incredibly easy to use and delivers improved clarity and strength. Compatible with all shrink-wrap machines, it offers a wide operating window, making it suitable for a diverse range of applications.

## SIGNIFICANT PROPERTIES

### General Properties

- Opacity for Light-Sensitive Products.
- Maintains confidentiality and privacy.
- Good tear resistance provides a safe & durable wrap on products.
- High tensile strength makes it suitable for product bundling.
- Compatible with all Shrink Wrap Machines.

### Sealing Properties

- Crosslinked Technology provides consistent sealing.
- Wide sealing temperature range.
- Strong and Durable seals.
- Less Residue.

### Shrinking Properties

- Balanced shrink for tight and crisp packages.
- Excellent cleanup for tight, attractive packages.
- High shrink force conforms to irregular shapes.
- Stronger heat resistance and cold resistance.

Bagla Group Shrink Films comply with the requirements and regulations of FDA and USDA which states that materials may be used in food contact applications.

## STANDARD PUT-UPS

- Available Thickness: 40 gauge
- Single Wound Flat Film is available in custom widths from 3" to 100" in 1/4" increments.
- Center Folded Film is available in custom widths from 3" to 50" in 1/2" increments.
- Shrink Pouches are available in lengths of 4" to 80" and openings of 4" to 40".
- Center Folded Film has half the linear footage of single-wound flat film for the same thickness (in gauge) and roll dimensions.

## APPLICATIONS

- Retail packaging
- Industrial packaging
- Pallet wrapping
- Bundling, Multipacking & Unitizing Products
- Shrink Sleeving

# TECHNICAL SPECIFICATIONS

Properties	ASTM Test Method	Unit	Thickness (gauge)
			40
Haze	D1003	%	2
Gloss at 20°	D2457	GU	135
COF, Kinetic	D1894	gf	0.2
Shrinkage, 150°C (302°F)--10 Min	D1204	%(area)	80
Shrink Force (100°C)	D2838	g/in	80
Stiffness Modulus (avg)	D882	kpsi	60
Tensile Strength (avg)	D882	kpsi	15
Elongation (avg)	D882	%	125
WVTR	F1249	g/100 in <sup>2</sup> /24hr	1.9
Oxygen Transmission	D3985	cc/100 in <sup>2</sup> /24hr	855
PIR Content	Internal	-	30

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

## BX-Tinted - Linear Footage of Center Folded Shrink Film

Core I.D.(Inches)	Roll O.D.(Inches)	40 gauge (Feet)
3	9 <sup>1/2</sup>	6,560
3	13	13,120
6	11	6,560
6	14	13,120
6	18 <sup>3/4</sup>	26,240

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in gauge) and roll dimensions.

## DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill

## STORAGE

- Storage below 32 degrees Celsius (90 degrees Fahrenheit) is recommended.



## DISCLAIMER

Bagla® films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

### Head Office

- New Delhi, Delhi

### Factories

- 3 in Mundra, Gujarat, India
- 2 in Roorkee, Uttar Pradesh, India
- 1 in Ghaziabad, Uttar Pradesh, India

### Domestic Sales Office

- Delhi • Mumbai • Kolkata • Cochin
- Bangalore • Hyderabad • Chennai • Bhopal

### International Sales Office

- Spain • USA • Australia • United Kingdom
- Argentina • South Africa • Egypt
- Poland • Germany • Canada