



Product Description:

EzeeTear Lite is manufactured from **23-micron High Tensile polypropylene (HTPP) film** coated with an acrylic adhesive system and a silicon release coating. This high tensile tear tape offers good initial tack, excellent shear resistance, and strong adhesion.

Product Specifications:

Properties	Test Method	Unit	Specification
Tap Width Tolerance	Bagla Internal Method	mm	± 0.1
Total Tapethickness	AFERA 5006	µm	34 ± 2
Film Thickness	AFERA 5006	µm	23 ± 2
Glue Thickness	Weight	GSM	11 ± 2
Breaking Strength	AFERA 5004	kgf/25mm	≥12
Elongation At Break	AFERA 5004	%	14 ± 5
Tensile Strength At Break	AFERA 5004	kgf/mm ²	18 ± 5
Peel Adhesion To Stainless Steel	FINAT FTM 1	gf/25mm	400 ± 10%
Loop Tack To Glass	FINAT FTM 9	gf/25mm	400 ± 10%

Standard Putups

- **Width:** 2mm to 30mm
- **Length:** 5,000m to 1,20,000m
- **Core ID:** 29, 76, 82.5, 125mm
- **Colors:** Clear + Multiple Colors
- **Wounding:** Traverse wound

Features

- Cost Effective Option
- Easy Opening
- Great Application performance
- Utilise print for increased consumer engagement

Applications

- Security applications
- Used in Cigarette Boxes Etc.
- Extensively used in tobacco, medicine, food, cosmetic industry

Additional Information

SHELF LIFE: The standard shelf life is 12 months from the date of manufacture. However, this depends on several factors such as storage conditions, handling etc.

DISPOSAL: Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

STORAGE: Storage below 32°C (90°F) is recommended.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.