



## Product Description:

**EzeeTear Plus** is manufactured from **26-micron High Tensile Polypropylene (HTPP) film** coated with an acrylic adhesive system and a silicon release coating. This tear tape offers good initial tack, excellent shear resistance, strong adhesion and is a cost-effective option as well.

## Product Specifications:

Properties	Test Method	Unit	Specification
Backing	-	-	HTPP
Slit Width Tolerance	Bagla Internal Method	mm	± 0.10
Total Tape Thickness	AFERA 5006	µm	35 ± 10%
Film Thickness	AFERA 5006	µm	26 ± 10%
Glue Thickness	Weight	GSM	10 ± 2
Tensile Strength	ASTM D3759	Kgs/ 25mm	13 ± 10%
Elongation at Break	ASTM D3759	%	75 ± 10%
Peel Adhesion	ASTM D 3330	G/25 MM	400 ± 100
Unwind Tension	ASTM D 3330	G/25 MM	Max.10

### Standard Putups

- **Width:** 1.5mm to 4mm
- **Length:** 5kms to 100kms
- **Core ID:** Customized
- **Colors:** Can be customizable
- **Wounding:** Traverse wound

### Features

- Cost-effective option.
- Easy opening.
- Great application performance.
- Utilise print for increased consumer engagement.

### Applications

- Extensively used in tobacco, medicine, food, cosmetic industry.

## Additional Information

**SHELF LIFE:** The standard shelf life is 36 months from the date of manufacture. However, this depends on several factors such as storage conditions, handling etc.

**DISPOSAL:** Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

**STORAGE:** Storage below 32°C (90°F) is recommended.

**DISCLAIMER:** The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.