

WrapTek Earth represents a significant leap forward in sustainable packaging solutions. This innovative film incorporates 60% Recycled Content (30% PCR, 30% PIR), reducing reliance on virgin plastic and minimizing environmental footprint. Additionally, it boasts AENOR Certification, a testament to its compliance with stringent European regulatory standards.

SIGNIFICANT PROPERTIES



General Properties

- High gloss, clarity, and transparency.
- Good tear resistance provides a safe & durable wrap on products.
- High tensile strength makes it suitable for product bundling.
- Compatible with all shrink wrap machines.



Sealing Properties

- Ensures strong & durable seals.
- Operates on a wide sealing temperature range.
- Superior ease of use manually as well on high-speed automatic shrink equipment.



Shrinking Properties

- High shrink force for bundling and multipacking.
- Superior puncture resistance to protect your products effectively.
- Excellent shrink performance for secure and tamper-evident seal.

STANDARD PUT-UPS

- Available Thickness: 10, 11, 15, 19, 25, 30, 38 microns in Cross Linked Variants and 12,15,19, 25, 30 microns in non cross linked variants.
- Single Wound Flat Film is available in custom widths from 75mm to 2540mm in 6.5mm increments.
- Center Folded Film is available in custom widths from 75mm to1270mm in 13mm increments.
- Pouches are available in lengths of 100mm to 2000mm and openings of 100m to 1000mm
- Avaliable as hot perforated and printed options as well.

APPLICATIONS

- Retail packaging
- Industrial packaging
- Bundling, Multipacking & Unitizing Products









TECHNICAL SPECIFICATIONS

| Donastics | ASTM Test Method | Unit | Cross Linked POF Shrink Film Thickness (Microns) | | | | | | |
|-----------------------------------|---------------------|-------------------------|--|-------|------|-------|-------|-------|-------|
| Properties | | | 10 | 11 | 15 | 19 | 25 | 30 | 38 |
| Haze | D1003 | % | 2 | 2 | 2.5 | 2.5 | 3 | 3 | 3 |
| Gloss at 20° | D2457 | GU | 135 | 135 | 135 | 135 | 130 | 130 | 130 |
| COF, Kinetic | D1894 | gf | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 |
| Shrinkage, 102°C (216°F)10 Min | D1204 | %(area) | 50 | 50 | 50 | 50 | 50 | 50 | 50 |
| Shrink Force (100°C) | D2838 | N/mm | 0.03 | 0.032 | 0.05 | 0.055 | 0.061 | 0.077 | 0.077 |
| Stiffness Modulus (avg) | D882 | MPa | 413 | 413 | 413 | 413 | 379 | 379 | 344 |
| Tensile Strength (avg) | D882 | MPa | 103 | 103 | 103 | 103 | 103 | 103 | 103 |
| Elongation (avg) | D882 | % | 125 | 130 | 145 | 150 | 160 | 160 | 170 |
| WVTR | F1249 | g/h.m²/24hr | 29.4 | 32.5 | 23.2 | 21.7 | 15.5 | 13.9 | 12.4 |
| Oxygen Transmission | D3985 | cc/m ² /24hr | 55.1 | 58 | 38.6 | 32.2 | 25.8 | 25.8 | 19.3 |
| PCR Content | Internal | - | 60 | 60 | 60 | 60 | 60 | 60 | 60 |

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

WrapTek Earth - Linear Footage of Center Folded Shrink Film

| With prock Earth - Effect 1 outage of oction 1 outed offinite 1 min | | | | | | | | | | |
|---|-------------------|----------------|-------|-------|-------|-------|-------|-------|--|--|
| Core I.D. | Roll O.D. (mm) | Length (Meter) | | | | | | | | |
| (mm) | | 10µm | 11µm | 15µm | 19µm | 25µm | 30µm | 38µm | | |
| 76 | 242 | 2,000 | 1,777 | 1,334 | 1,067 | 800 | 664 | 533 | | |
| 76 | 330 | 4,000 | 3,554 | 2,667 | 2,134 | 1,600 | 1,329 | 1,067 | | |
| 152 | 280 | 2,000 | 1,777 | 1,334 | 1,067 | 800 | 664 | 533 | | |
| 152 | 356 | 4,000 | 3,554 | 2,667 | 2,134 | 1,600 | 1,329 | 1,067 | | |
| 152 | 476 | 8,000 | 7,108 | 5,334 | 4,267 | 3,200 | 2,658 | 2,134 | | |

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in micron) and roll dimensions.

DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill

















STORAGE



Fahrenhiet) is recommended.



• Storage below 32 degrees Celsius (90 degrees

DISCLAIMER

Bagla Group films technical data is based on reliable tests & information. Still, users should not solely rely on this advice for specific applications, as performance properties may vary based on processing conditions. Users assume this information at their own risk & independent confirmation of its validity and suitability for specific cases is recommended. Bagla Group does not guarantee results & assumes no liability in connection with its advice. This publication does not grant a license to operate or recommend patent infringement.

Head Office

New Delhi

Factories

- 3 in Mundra, India
- 1 in Kolkata, India
- 1 in Dadri, India
- 1 in Ciudad del Este, Paraguay
- 1 in Surabaya, Indonesia

Domestic Sales Office

- Delhi Mumbai Kolkata Cochin
- Bangalore Hyderabad Chennai Bhopal

Key Markets

- USA Canada Mexico Germany
- UK France Italy Spain
- Poland Brazil Argentina Australia

