



Product Description:

EzeeRip is produced from **75-micron monoaxially oriented polypropylene (MOPP) film** and coated with a newly formulated pressure-sensitive adhesive. It is suitable for easy opening of packaging including corrugated cases, fibreboard cartons, envelopes, paper sacks, and e-commerce mailers.

Product Specifications:

Properties	Test Method	Unit	Specification
Tape Width Tolerance	Bagla Internal Method	mm	± 0.1
Total Tape Thickness	AFERA 5006	μm	100 ± 10
Film Thickness	AFERA 5006	μm	75 ± 5
Glue Thickness	Weight	GSM	25 ± 2
Breaking Strength	AFERA 5004	N/cm	≥ 54
Elongation at Break	AFERA 5004	%	≥ 30
Tensile Strength at Break	AFERA 5004	kgf/mm ²	≥ 36
Peel Adhesion to Stainless Steel	FINAT FTM 1	gf/25mm	≥ 800
Loop Tack to Glass	FINAT FTM 9	gf/25mm	≥ 800

Standard Putups

- **Width:** 3mm to 25mm
- **Length:** 5,000m to 120,000m
- **Core ID:** 76mm, 152mm
- **Colors:** Clear + Multiple Colors
- **Wounding:** Traverse wound

Features

- Rips easily through most grades of fluting and board.
- Enhances product strength & reinforces the weaker areas.
- Utilise print for increased consumer engagement.

Applications

- Opening of corrugated boxes & fibreboard cartons
- Ideal for solid fiberboards ranging from 200–600 g/m²

Additional Information

SHELF LIFE: The standard shelf life of our tear tapes is 12 months, but if kept in optimal conditions, the tear tapes can be used upto 36 months.

DISPOSAL: Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

STORAGE: Storage below 32°C (90°F) is recommended.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.