



Product Description:

EzeeTear Lite is manufactured from **26-micron High Tensile polypropylene (HTPP) film** coated with an acrylic adhesive system and a silicon release coating. This high tensile tear tape offers good initial tack, excellent shear resistance, and strong adhesion.

Product Specifications:

Properties	Test Method	Unit	Specification
Tap Width Tolerance	Bagla Internal Method	mm	± 0.1
Total Tapethickness	AFERA 5006	μm	37 ± 2
Film Thickness	AFERA 5006	μm	26 ± 2
Glue Thickness	Weight	GSM	11 ± 2
Breaking Strength	AFERA 5004	kgf/25mm	≥ 24
Elongation At Break	AFERA 5004	%	16.5 ± 5
Tensile Strength At Break	AFERA 5004	kgf/mm ²	22 ± 2
Peel Adhesion To Stainless Steel	FINAT FTM 1	gf/25mm	$400 \pm 10\%$
Loop Tack To Glass	FINAT FTM 9	gf/25mm	$400 \pm 10\%$

Standard Putups	Features	Applications
Width: 2mm to 30mm Length: 5,000m to 1,20,000m Core ID: 29, 76, 82.5, 125mm Colors: Clear + Multiple Colors Wounding: Traverse wound	- Cost Effective Option - Easy Opening - Great Application performance - Utilise print for increased consumer engagement	- Security applications - Used in Cigarette Boxes Etc. - Extensively used in tobacco, medicine, food, cosmetic industry

Additional Information

SHELF LIFE: The standard shelf life is 12 months from the date of manufacture. However, this depends on several factors such as storage conditions, handling etc.

DISPOSAL: Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

STORAGE: Storage below 32°C (90°F) is recommended.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.