



Product Description:

EzeeTear Plus is manufactured from **26-micron High Tensile Polypropylene (HTPP) film** coated with an acrylic adhesive system and a silicon release coating. This tear tape offers good initial tack, excellent shear resistance, strong adhesion and is a cost-effective option as well.

Product Specifications:

Properties	Test Method	Unit	Specification
Backing	-	-	HTPP
Slit Width Tolerance	Bagla Internal Method	mm	± 0.10
Total Tape Thickness	AFERA 5006	μm	$35 \pm 10\%$
Film Thickness	AFERA 5006	μm	$26 \pm 10\%$
Glue Thickness	Weight	GSM	10 ± 2
Tensile Strength	ASTM D3759	Kgs/ 25mm	$13 \pm 10\%$
Elongation at Break	ASTM D3759	%	$75 \pm 10\%$
Peel Adhesion	ASTM D 3330	G/25 MM	400 ± 100
Unwind Tension	ASTM D 3330	G/25 MM	Max.10

Standard Putups

- **Width:** 1.5mm to 4mm
- **Length:** 5kms to 100kms
- **Core ID:** Customized
- **Colors:** Can be customizable
- **Wounding:** Traverse wound

Features

- Cost-effective option.
- Easy opening.
- Great application performance.
- Utilise print for increased consumer engagement.

Applications

- Extensively used in tobacco, medicine, food, cosmetic industry.

Additional Information

SHELF LIFE: The standard shelf life is 12 months from the date of manufacture. However, this depends on several factors such as storage conditions, handling etc.

DISPOSAL: Preferred options for disposal are: (1) recycling, SPI Code 7; (2) incineration with energy recovery; and (3) land fill.

STORAGE: Storage below 32°C (90°F) is recommended.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.