



WrapTek Earth represents a significant leap forward in sustainable packaging solutions. This innovative film incorporates 60% Recycled Content (30% PCR, 30% PIR), reducing reliance on virgin plastic and minimizing environmental footprint. Additionally, it boasts AENOR Certification, a testament to its compliance with stringent European regulatory standards.

SIGNIFICANT PROPERTIES



General Properties

- High gloss, clarity, and transparency.
- Good tear resistance provides a safe & durable wrap on products.
- High tensile strength makes it suitable for product bundling.
- Compatible with all shrink wrap machines.



Sealing Properties

- Ensures strong & durable seals.
- Operates on a wide sealing temperature range.
- Superior ease of use manually as well on high-speed automatic shrink equipment.



Shrinking Properties

- High shrink force for bundling and multipacking.
- Superior puncture resistance to protect your products effectively.
- Excellent shrink performance for secure and tamper-evident seal.

STANDARD PUT-UPS

- Available Thickness: 10, 11, 15, 19, 25, 30, 38 microns in Cross Linked Variants and 12,15,19, 25, 30 microns in non cross linked variants.
- Single Wound Flat Film is available in custom widths from 75mm to 2540mm in 6.5mm increments.
- Center Folded Film is available in custom widths from 75mm to 1270mm in 13mm increments.
- Pouches are available in lengths of 100mm to 2000mm and openings of 100mm to 1000mm
- Available as hot perforated and printed options as well.

APPLICATIONS

- Retail packaging
- Industrial packaging
- Bundling, Multipacking & Unitizing Products



TECHNICAL SPECIFICATIONS

Properties	ASTM Test Method	Unit	Cross Linked POF Shrink Film Thickness (Microns)						
			10	11	15	19	25	30	38
Haze	D1003	%	2	2	2.5	2.5	3	3	3
Gloss at 20°	D2457	GU	135	135	135	135	130	130	130
COF, Kinetic	D1894	gf	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Shrinkage, 102°C (216°F)--10 Min	D1204	%(area)	50	50	50	50	50	50	50
Shrink Force (100°C)	D2838	N/mm	0.03	0.032	0.05	0.055	0.061	0.077	0.077
Stiffness Modulus (avg)	D882	MPa	413	413	413	413	379	379	344
Tensile Strength (avg)	D882	MPa	103	103	103	103	103	103	103
Elongation (avg)	D882	%	125	130	145	150	160	160	170
WVTR	F1249	g/h.m²/24hr	29.4	32.5	23.2	21.7	15.5	13.9	12.4
Oxygen Transmission	D3985	cc/m²/24hr	55.1	58	38.6	32.2	25.8	25.8	19.3
PCR Content	Internal	-	60	60	60	60	60	60	60

Note: These values are typical data for Bagla-Group shrink film and are not product release specifications, warranties or limiting specifications. Values are based on initial production and tests run during development of this film.

WrapTek Earth - Linear Footage of Center Folded Shrink Film

Core I.D. (mm)	Roll O.D. (mm)	Length (Meter)						
		10µm	11µm	15µm	19µm	25µm	30µm	38µm
76	242	2,000	1,777	1,334	1,067	800	664	533
76	330	4,000	3,554	2,667	2,134	1,600	1,329	1,067
152	280	2,000	1,777	1,334	1,067	800	664	533
152	356	4,000	3,554	2,667	2,134	1,600	1,329	1,067
152	476	8,000	7,108	5,334	4,267	3,200	2,658	2,134

Note: Single Wound Film has double the linear footage of center-fold film for the same thickness (in micron) and roll dimensions.

DISPOSAL

- Recycle (Dry or Wet processing to extrude into pellets)
- Waste to Energy (WtE) through incineration (most desirable)
- Land fill

STORAGE

- Storage below 32 degrees Celsius (90 degrees Fahrenheit) is recommended.



ADDITIONAL INFORMATION

SHELF LIFE: The typical shelf life of our POF Shrink Films is about 5 years when stored properly.

DISCLAIMER: The technical data contained herein are guides to the use of Bagla® products. Bagla Group makes no guarantees of results and assumes no obligations or liability in connection with its advice.

Head Office

- New Delhi

Factories

- 3 in Mundra, India
- 1 in Kolkata, India
- 1 in Dadri, India
- 1 in Ciudad del Este, Paraguay
- 1 in Surabaya, Indonesia

Domestic Sales Office

- Delhi • Mumbai • Kolkata • Cochin
- Bangalore • Hyderabad • Chennai • Bhopal

Key Markets

- USA • Canada • Mexico • Germany
- UK • France • Italy • Spain
- Poland • Brazil • Argentina • Australia

bagla GROUP | Let's innovate Packaging!