

# MEDIUM BARRIER WHITE THERMOFORMING FILM

Ideal for food products with a shorter shelf life, Medium Barrier thermoforming films are made from combinations of materials such as Polyethylene (PE) and Polyamide (PA). They are helpful for products like fresh fruits and vegetables, some processed foods, and products requiring moderate protection. Thickness can range from 80 µm upto 300 µm.



## TECHNICAL SPECIFICATIONS

PHYSICAL PROPERTIES		UNIT	TEST METHOD	VALUE												
Gauge		µm	ASTM F2251	80	90	100	125	150	175	200	225	250	275	300		
Yield		m <sup>2</sup> /kg	-	0.0129	0.0115	0.0104	0.0083	0.0069	0.0059	0.0052	0.0046	0.0041	0.0038	0.0035		
Tensile Strength	MD	MPa	ASTM D882	39	37	36	34	32	31	30	29	29	28	28		
	TD			35	34	33	31	30	30	29	29	28	28	28		
Elongation	MD	%	ASTM D882	450												
	TD			450												
COF		-	ASTM D1894	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	
THERMAL PROPERTIES																
Seal Strength		N/15	ASTM F88	25	27	30	35	40	45	50	55	60	65	70		
OPTICAL PROPERTIES																
Opacity		%	ASTM D589	>80	>80	>80	>85	>85	>85	>85	>85	>85	>85	>85	>85	
Gloss @ 60°		GU	ASTM D2457	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	
BARRIER PROPERTIES																
OTR		cc/ m <sup>2</sup> .d.bar	ASTM D3985	11.0	9.0	7.5	5.0	3.5	2.5	2.0	1.7	1.5	1.5	1.5	1.5	
WVTR		g/m <sup>2</sup> .d	ASTM F1249	9.5	8.5	7.5	6.0	5.0	4.5	4.0	3.5	3.0	3.0	3.0	3.0	

## ADDITIONAL INFORMATION

### Application

This product can be frozen or boiled in water and the recommended application temperature is less than 95 °C. All the raw material for manufacturing these barrier films meets the requirement of USFDA, EU/10/2011, and FSSAI, thus ensuring food safety at all times.

### Equipment Parameters

Pre-heat temperature 90~100°C; Pre-heat time 1~2s; Sealing temperature 135~145°C, Sealing time 1~2s.

### Storage & Shelf Life

This barrier film should ideally be placed in a clean, cool and dry area where it does not come in direct contact with mordant chemical goods and or any other injurant.

The product shelf life is 12 months from the date of dispatch. To protect the properties of the film, it is advisable to store it in dry and hygienic conditions, away from moisture and direct sunlight.

### Disclaimer

The technical information provided by Bagla Group is intended as general guidance only. While the data and recommendations are based on our testing and are believed to be accurate and reliable, they should not be considered a substitute for user evaluation. Performance characteristics may vary depending on processing conditions and specific applications. Users are advised to independently verify the suitability and effectiveness of the product for their intended use. Bagla Group assumes no liability for outcomes resulting from the use of this information.